

X-Tech EpoxySeal FLR110G

Chemical resistant high build epoxy floor coating

Product Description

X-Tech EpoxySeal FLR110G is a high performance, high build, solvent free epoxy floor coating that is also decorative and suitable for use in a wide range of applications. It can also be used as a wall coating.

Advantages

- High abrasion resistance
- Resistant to wide range of chemicals
- Smooth and anti-slip finish available
- Easy to clean and maintain

Uses

- Car park decks
- Process areas
- Pharmaceutical, food and beverage plants
- Storage areas
- Stairwells

Labratory Test Data

Property	Typical Results
Compressive strength (ASTM D695)	>85MPa
Flexural strength (ASTM D790)	>40MPa
Abrasion resistance (ASTM D4060-CS10)	<50mg loss/1000 cycles
Impact resistance (ASTM D2794)	No cracking
Bond to concrete (ASTM D4541)	>2MPa
Tensile Strength (ASTM D638)	>30Mpa
Shore Hardness (ASTM D2240)	81

Volatile Organic Content

X-Shield SF Primer = <50g/L
X-Shield MT Primer = <50g/L
X-Tech EpoxySeal FLR110G = <50g/L

Application Properties

Application thickness (2 coats)	200 to 300 microns
Application temperature range	10 to 35C (50 to 95F)
Pot life at 25c	
X-Shield SF Primer	30 mins
X-Shield MT Primer	120 mins
X-Tech EpoxySeal FLR110G	40 mins
Recoat time	18 to 24 hours at 25c
Full cure	7 days at 25C

Chemical Resistance

X-Tech EpoxySeal FLR110G has excellent resistance to the following chemicals:

White spirit	Oils
20% Sulphuric acid	Petrol
Concentrated bleach	
Saturated sugar solution	

Colors

RAL 7001 Silver Grey	RAL 5017 Traffic Blue
RAL 6029 Mint Green	RAL 1001 Beige
RAL 7035 Light Grey	RAL 3002 Carmine Red

Others colours available on request.

Theoretical Coverage

X-Tech EpoxySeal FLR110G: 4 - 4.5 m²/Kg per coat.
Dry film thickness of 150 to 200 microns
Actual coverage will depend on wastage and surface profile and can be up to 20% or more higher than theoretical coverage.

Packaging

X-Tech EpoxySeal FLR110G: 1 , 5 and 20 Kg pack.

Shelf Life

12 months when stored below 30C under shade in a dry environment.

Installation Guidelines

X-Tech EpoxySeal FLR110G should be applied by experienced coating crews. NCC X-Calibur provides detailed method statements on all its products for use in various applications. These must be referred to prior to starting work. The information below is a summary intended for guidance only.

Surface Preparation

The substrate must be structurally sound. Loose or unsound concrete should be removed and made good. Surfaces must be entirely free of oil, grease, paint, corrosion deposits, dust, laitance or other surface deposits. The surface should be prepared by captive blasting to produce a lightly exposed aggregate surface i.e. a ICRI CSP 4 or 5 surface profile. Any bug holes (blow holes) should be filled with X-Shield BugFill or X-Shield Primer Filler (when using X-Shield MT Primer apply BugFill or Primer Filler after priming). If substrate is not level or is uneven, level using X-Tech LevelCem HD.

Moisture Testing

The concrete slab should be tested for moisture with the Rapid RH system following the procedure in ASTM F2170. If the humidity reading is greater than 80% then conduct moisture vapor emission rate (MVER) testing using the procedure in ASTM F1869. (Both test kits are available for purchase from X-Calibur). If the MVER Primer is 3 to 5 lbs/1000ft²/24h use a single coat X-Shield MT Primer at 165 microns wft. If the MVER is 5 to 12 lbs/1000ft²/24h use two coats of X-Shield MT Primer at 200 microns wft per coat.

Priming

Prime with X-Shield SF Primer or X-Shield MT Primer and allow to dry before applying X-Tech EpoxySeal FLR110G. The base and hardener have to mixed using a slow speed drill and approved mixing paddle until homogenous. The mixed primer should then be applied to the prepared substrate with a polyurethane squeegee and back rolled with a short hair roller (NCC X-Calibur velvet roller or similar). Do not over apply or allow puddles of primer to form. If the primer is absorbed into the surface easily, it will be necessary to apply a second coat once the initial coat is tack-free. Allow the primer to become tack-free before application of X-Tech EpoxySeal FLR110G. Apply X-Tech EpoxySeal FLR110G within the recoat window.

Mixing

Add the hardener to the base and mix using a slow speed drill with an X-Shield Coating Mixer. Paddle for 3 minutes until both components have fully dispersed and are uniform in color. Be sure to rotate the mixer throughout the drum. Mix only full packs.

Application

Apply in two coats of 100 to 175 microns per coat wet film thickness using short hair roller or airless spray. Recoat after 18 to 24 hours at 25C

Slip Resistant Finish

A slip resistant finish can be achieved by broadcasting X-Tech Anti Skid Grains onto the surface of the first coat while still wet. The grain size (Fine, Medium or Coarse) and broadcast rate will depend on the surface texture required but will generally be in the range of 0.5 to 1kg/m².

Limitations

May change color when exposed to direct sunlight.
Do not be apply within 3C of the dewpoint or if it is within 5C of the dewpoint and dropping.
Avoid excessive application.
Avoid skin contact.
Do not apply below 10C.
Do not discard into the water system.
Protect from chemical and water spillage until fully cured.

Health and Safety

This product is for industrial use only by trained operatives. It is potentially hazardous if not used correctly. Please refer to the Material Safety Data Sheet (MSDS) prior to the purchase and use of this product. The MSDS can be obtained via our website www.ncc.com.eg

Authorized Technical Specialist

Please note that only NCC X-Calibur Authorized Technical Specialists ('ATSS') are permitted to change any of the information in this data sheet or to provide written recommendations concerning the use of this product. Visit www.ncc.com.eg for a full list of NCC X-Calibur ATSSs.

Datasheet Validity

NCC X-Calibur makes modifications to its product datasheets on a continuous basis. Please check the datasheet update section on www.ncc.com.eg to ensure you have the latest version.

Warranties

NCC X-Calibur supplies products that comply with the proper-ties shown on the current datasheets. In the unlikely event that products supplied are proved not to comply with these properties, then we will replace the non-compliant product or refund the purchase price. X-Calibur does not warrant or guarantee the installation of the products as it does not have control over the installation or end use of the products. Any suspected defects must be reported to NCC X-Calibur in writing within five working days of being detected. NCC X-Calibur Construction Chemicals **makes no warranty as to merchantability or fitness for a particular purpose and this warranty is in lieu of all other warranties express or implied.** NCC X-Calibur Construction Chemicals shall not be liable for damages of any sort including remote or consequential damages, down time, or delay.